HESKINS
ANTI-SLIP SOLUTIONS
mail@heskins.com www.heskins.com 07/04/2021

# Heskins H3450 coarse resilient data sheet, MK3

| Subject | Result |
|---|---|
| **Composition** | Composite construction |
| **Type of adhesive** | Solvent acrylic |
| **Overall thickness (mm)** | 1.19mm |
| **Tackloop (kg/25.4mm)** | 2.88 |
| **Cohesion (mins/25°C)** | 4320 |
| **Adhesion to steel (kg/25.4mm)** | 2.3 |
| **Applied Weight** | 865 g/m² |
| **Temperature range** | -10°C ~ 80°C |
| **Maximum roll size** | 1346mmx100m |
| **Life (months)** | 12 to 24 |

## LRV Test Results

| Material/Colour | Av. LRV | Range |
|---|---|---|
| H3450N (Black) | 0 | 0 |
| H3450S (Grey) | 6 | 2 |
| H3450B (Blue) | 3.5 | 1 |
| H3450T (Transparent) | 51.5 | 3 |
| H3450W (White) | 85 | 3 |

## Coefficient of friction data

| | Dry surface test result | Wet surface test result |
|---|---|---|
| **H3450 Coarse resilient** | 102 TRL | 47 TRL |

*The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.*

All the above data is for reference only.

**©Heskins Ltd 1997-2021**

ISO 9001 CERTIFIED British Assessment Bureau
ISO 14001 CERTIFIED British Assessment Bureau